

Suitable corrosivity categories/durability ranges

| Paint system ISO 12944-5 | Low | Medium | High | Very high |
|-----------------------------|-----|--------|------|--------------|
| C2.01 | Х | | | |

TEC2.01 Low

TEKNOSYNT PRIMER 3 Paint systems 80 µm

1 1.8.2018

TEKNOSYNT PRIMER 3 paint systems consist of white spirit containing thixotropic paints, that contain active anticorrosive pigments.

These paint systems can be used in field and station painting of structured steel objects.

These paint systems are designed for corrosivity category C2 with durability class low.

| Paint | | D1 | D2 |
|------------------------|----|---------|---------|
| TEKNOSYNT PRIMER 3 | AK | 1x40 µm | 1x40 µm |
| TEKNOSYNT COMBI 50 | AK | 1x40 µm | |
| TEKNOSYNT 90 | AK | | 1x40 µm |
| Total film thickness | | 80 µm | 80 µm |
| Paint system VOC, g/m² | | 74 | 84 |

| Example of Teknos paint system code | Example of paint system structure | |
|-------------------------------------|--|--|
| TEC2.01/L/ D1 | ISO 12944-5/C2.01-AK (AK80/2-FeSa 2½). | |

These Teknos painting systems have been designed in accordance with ISO 12944:2017-2018 standards. In order to reach the durability ranges in specified corrosivity categories, care must be taken to ensure full compliance of steel construction design, steel prework and surface preparation quality with ISO 12944 standards.

Surface preparation Remove from the surfaces any contaminants that might be detrimental to surface preparation and painting. Remove also water-soluble salts by using appropriate methods.

Steel surfaces: Remove mill scale and rust by blast cleaning to preparation grade Sa 2½ (standard ISO 8501-1).

For more detailed information about of the above-mentioned products please see individual product data sheets.