

# FLOOR 4500-10

## Water-soluble 1C floor sealing coating for interior use

FLOOR 4500 is a water-soluble, highly abrasion-resistant 1C floor sealing coating for low-emission, odourless treatment of practically all softwoods and hardwoods. FLOOR 4500 is also suitable as a top sealing coating on MINOPRIMER AQUA 6700 for anhydrite floors. The product is resistant to light and yellowing.





#### **TECHNICAL DATA**

| Certificates, approvals and<br>classification | Swiss environmental label UE II, class C, EMICODE EC 1 Plus  |
|---|--|
| Fields of application                         | Floors   |
| Solids  | Approx. 32% by weight  |
| Volatile organic compound (VOC)               | Approx. 79 g/l (DIRECTIVE 2010/75/EU)  |
|   | The VOC value provided is the average value for factory produced products, and   |
|   | consequently it will be subject to variations between individual products  |
|   | covered by this Technical Data Sheet.  |
| Theoretical spreading rate                    | 120 g/m²; 8.3 m²/kg  |
| Colours                                       | Colourless.  |
| Tinting system                                | Largo  |
| Gloss (60°)                                   | 10   |
| Density                                       | Approx. 1.03 g/ml  |
| Storage                                       | Storage temperature is +5°C - +30°C. Store in a tightly closed container.  |
| DIRECTION FOR USE                             |  |
| Surface preparation                           | Every substrate must be well-cleaned, dry and free from grease and oil. Coating removal: Sand  |
| Application method                            | Brush, Roller  |
|   | When renovating or coating exotic wood species, we recommend using RENO  |
|   | GRUND 3300.  |
|   | Do not use on pear wood without a primer. Risk of film formation faults.   |
|   | When using on dark woods please refer to the instructions in our VTM 5564<br>"White discolouration" in the areas around the joints of sealed dark wood floors. |



| Application            | Stir or shake the proo<br>machine. | duct well for several minutes before use   | e, if necessary by   |  |  |
|------------------------|------------------------------------|--|----------------------|--|--|
|                        |                                    | APPLICATION ADVICE   |                      |  |  |
|                        | Intensification of parquet         | Intensification of parquet   |                      |  |  |
|                        |                                    | Product  | Applied Quantity     |  |  |
|                        | Primer                             | RENO GRUND 3300  | 125 g/m²             |  |  |
|                        | or                                 | PARKETTGRUND 4510  | 120 g/m²             |  |  |
|                        | Recoating                          | FLOOR 4500   | 120 g/m²             |  |  |
|                        | Intermediate sanding               | With grain 120-150   |                      |  |  |
|                        | Recoating                          | FLOOR 4500   | 120 g/m²             |  |  |
|                        | Parquet not grain-accentua         | Parquet not grain-accentuating   |                      |  |  |
|                        |                                    | Product  | Applied Quantity     |  |  |
|                        | Primer                             | PARKETT RENO GRUND NORDIC 3338   | 125 g/m²             |  |  |
|                        | or                                 | NATURGRUND 4538  | 120 g/m²             |  |  |
|                        | Recoating                          | FLOOR 4500   | 120 g/m²             |  |  |
|                        | Intemrediate sanding               | With grain 120-150   |                      |  |  |
|                        | Recoating                          | FLOOR 4500   | 120 g/m²             |  |  |
|                        | Prepared, stable substrate (       | Prepared, stable substrate (anhydrite floors)  |                      |  |  |
|                        |                                    | Product  | Applied Quantity     |  |  |
|                        | Primer                             | MINOPRIMER AQUA 6700   | 150 g/m²             |  |  |
|                        | Recoating                          | FLOOR 4500   | 120 g/m²             |  |  |
|                        | Intermediate sanding               | using a green pad (sia brand)  |                      |  |  |
|                        | Recoating                          | FLOOR 4500   | 120 g/m²             |  |  |
|                        | For fu                             | irther application proposals please ask our represent  | ative.               |  |  |
| Application conditions | apply below +10°C. I               | Recommended temperature for surroundings and product: +15°C-25°C. Do not<br>apply below +10°C. Ideal surface and object temperature for application:<br>+18°C-22°C. Avoid application in direct sunlight. Underfloor heating systems |                      |  |  |
|                        | must be adjusted we                | must be adjusted well in advance.  |                      |  |  |
| Drying time            | +23°C / 65% RH                     | +23°C / 65% RH   |                      |  |  |
| - dust free            | after 2 hours                      |  |                      |  |  |
| - overcoatable         | after 4 hours                      | after 4 hours  |                      |  |  |
| - fit for sanding      | after 4 hours                      | after 4 hours  |                      |  |  |
| - through dry          | after 7 days                       | after 7 days   |                      |  |  |
|                        | When using non-slip                | carpet underlay please ensure that onl   | v qualities that are |  |  |
|                        | <b>-</b> .                         | orne coatings are used (contact supplier   |                      |  |  |
|                        |                                    | , , , , , , , , , , , , , , , , , , ,  |                      |  |  |

### **HEALTH AND SAFETY**

| Safety and precaution measures | See safety data sheet.  |
|--------------------------------|---|
| First aid                      | We recommend wearing personal protective clothing even in cases where no  |
|                                | local regulations are in force.   |
|                                | CH: The precautions according to local regulations (SUVA) with respect to |
|                                | hygiene and equipment must be observed.                                   |



#### **ADDITIONAL INFORMATION**

Maintenance instructions

Initial and maintenance care: After at least 3 weeks curing time with RENSA FLOOR POLISH 4580.

For more information on wood floor surface treatments and their use, visit www.parkett-verband.ch.

#### Teknos Group Oy Takkatie 3, P.O.Box 107 FI-00371 Helsinki, Finland Tel. +358 9 506 091

The above information is normative and based on laboratory tests and practical experiences. The information is noncommittal, and we cannot accept liability for the results obtained under working conditions beyond our control, and consequently the buyer or the user is not released from the obligation to test the suitability of our products for specific means and application methods under the actual application conditions. Our liability covers only damage caused directly by defects in the products supplied by Teknos. This product is intended for professional use only. This implies that the user possesses sufficient knowledge for using the product correctly with regard to technical and working safety aspects. The latest versions of Teknos' Technical Data Sheets and Safety Data Sheets are available from our homepage www.teknos.com. All trademarks displayed on this document are the exclusive property of Teknos Group or its affiliated companies.