

# FLOOR ANTIGLISS 4501-25

Water-soluble 1C floor sealing coating for interior use

FLOOR ANTIGLISS 4501 is a textured, water-soluble, highly abrasion-resistant 1C floor sealing coating for low-emission, odourless treatment of practically all softwoods and hardwoods. The product is resistant to light and yellowing.



## TECHNICAL DATA

<b>Certificates, approvals and classification</b>	Swiss environmental label UE II, class C
<b>Solids</b>	Approx. 33% by weight
<b>Theoretical spreading rate</b>	120 g/m <sup>2</sup> ; 8.3 m <sup>2</sup> /kg
<b>Colours</b>	Colourless.
<b>Tinting system</b>	Largo
<b>Gloss (60°)</b>	25
<b>Density</b>	Approx. 1.02 g/ml
<b>Storage</b>	Storage temperature is +5°C - +30°C. Store in a tightly closed container.

## DIRECTION FOR USE

<b>Surface preparation</b>	Every substrate must be well-cleaned, dry and free from grease and oil. Coating removal: Sand
<b>Application method</b>	When renovating or coating exotic wood species, we recommend using PARKETT RENO GRUND 3300.

Do not use on pear wood without a primer. Risk of film formation faults.

When using on dark woods please refer to the instructions in our VTM 5564 "White discolouration" in the areas around the joints of sealed dark wood floors.

<b>Application</b>	Stir or shake the product well for several minutes before use, if necessary by machine.	
<b>APPLICATION ADVICE</b>		
Raw parquet flooring		
	Product	Applied Quantity
Primer	Primer for parquet flooring	125 g/m <sup>2</sup>
Recoating	FLOOR 4501 ANTIGLISS	120 g/m <sup>2</sup>
Intermediate sanding	With grain 120-150	
Recoating	FLOOR 4501 ANTIGLISS	120 g/m <sup>2</sup>
For further application proposals please ask our representative.		

**Application conditions** Recommended temperature for surroundings and product: +15°C-25°C. Do not apply below +10°C. Ideal surface and object temperature for application: +18°C-22°C. Avoid application in direct sunlight. Underfloor heating systems must be adjusted well in advance.

<b>Drying time</b>	+23°C / 65% RH
<b>- overcoatable</b>	after 4 hours
<b>- fit for sanding</b>	after 4 hours
	When using non-slip carpet underlay please ensure that only qualities that are suitable for water-borne coatings are used (contact supplier or manufacturer).

**Cleaning** Wash the equipment immediately after use. VERDÜNNER 1000-98

## HEALTH AND SAFETY

<b>Safety and precaution measures</b>	See safety data sheet.
<b>First aid</b>	We recommend wearing personal protective clothing even in cases where no local regulations are in force. CH: The precautions according to local regulations (SUVA) with respect to hygiene and equipment must be observed.

## ADDITIONAL INFORMATION

**Maintenance instructions** Initial and maintenance care: After at least 3 weeks curing time with RENSA FLOOR POLISH 4580.

For more information on wood floor surface treatments and their use, visit [www.parkett-verband.ch](http://www.parkett-verband.ch).

**Teknos Group Oy Takkatie 3, P.O.Box 107 FI-00371 Helsinki, Finland Tel. +358 9 506 091**

The above information is normative and based on laboratory tests and practical experiences. The information is noncommittal, and we cannot accept liability for the results obtained under working conditions beyond our control, and consequently the buyer or the user is not released from the obligation to test the suitability of our products for specific means and application methods under the actual application conditions. Our liability covers only damage caused directly by defects in the products supplied by Teknos. This product is intended for professional use only. This implies that the user possesses sufficient knowledge for using the product correctly with regard to technical and working safety aspects. The latest versions of Teknos' Technical Data Sheets and Safety Data Sheets are available from our homepage [www.teknos.com](http://www.teknos.com). All trademarks displayed on this document are the exclusive property of Teknos Group or its affiliated companies.