

# MATTÖL BUNT 1409-15

Solvent-based, high-quality preservative oil for wood substrates for interior use



MATTÖL 1410 & MATTÖL BUNT 1409 are low-viscosity, matt preservative oils based on natural raw materials. The products have a good mechanical strength.

Parquet floors: For treating the surfaces of wooden floors, stairs and cork floors.

Carpenter application: For surface treatment of wooden doors, tables, chairs and stairs.



## TECHNICAL DATA

<b>Certificates, approvals and classification</b>	Swiss environmental label UE II, class F, EN 71-3
<b>Fields of application</b>	Furniture, Floors
<b>Recommended substrate</b>	Wood
<b>Solids</b>	Approx. 40% by weight
<b>Volatile organic compound (VOC)</b>	Approx. 529 g/l (DIRECTIVE 2010/75/EU) The VOC value provided is the average value for factory produced products, and consequently it will be subject to variations between individual products covered by this Technical Data Sheet.
<b>Theoretical spreading rate</b>	75 g/m <sup>2</sup> ; 13.3 m <sup>2</sup> /kg
<b>Colours</b>	Colourless. White. Black. Certain colours are delivered from stock. Can be adjusted individually for customers by agreement.
<b>Tinting system</b>	Largo
<b>Gloss (60°)</b>	15
<b>Hardener</b>	10% UNIPUR 279/1910-99 HÄRTER can be added to improve mechanical and chemical resistance. For colour shades (also white and black) the addition of UNIPUR 279/1910-99 HÄRTER is mandatory. This fixes the colouring agents additionally.
<b>Mixing ratio (A:B)</b>	10:1 parts by volume
<b>Pot life, +23 °C</b>	4 h
<b>Density</b>	Approx. 0.85 g/ml
<b>Storage</b>	Storage temperature is +5 °C - +30 °C. Store in a tightly closed container.

## DIRECTION FOR USE

**Surface preparation** Every substrate must be well-cleaned, dry and free from grease and oil. Coating removal: Sand

**Application method** Cloth, Smooth roller  
Hazard warning:  
Pads and cloths soaked in oil can spontaneously combust under certain conditions and should therefore be kept in a metal bin with a lid until they are disposed of correctly.

**Application** Stir or shake the product well for several minutes before use, if necessary by machine.

APPLICATION ADVICE		
Wood substrate raw - parquet		
	Product	Applied Quantity
Primer	MATTÖL 1409	depending on wood type 60-70 g/m <sup>2</sup>
	Apply lengthwise and across the fibre, allow to soak in only briefly and massage in with beige pad when wet.	
Recoating	MATTÖL 1409	depending on wood type 30-40 g/m <sup>2</sup>
	Apply lengthwise and across the fibre, allow to soak in only briefly and massage in with beige pad when wet.	
Wood substrate raw - carpenter application		
	Product	Applied Quantity
Primer	MATTÖL 1409	75 g/m <sup>2</sup>
	Apply lengthwise and across the fibre, allow to soak in only briefly and remove with a cloth when wet or massage in with beige pad.	
Intermediate sanding	Carefully sand with lacquer sandpaper 280-320 or with a beige pad	
Recoating	MATTÖL 1409	40 g/m <sup>2</sup>
	Apply lengthwise and across the fibre, allow to soak in only briefly and remove with a cloth when wet or massage in with beige pad.	
For further application proposals please ask our representative.		

**Application conditions** Recommended temperature for surroundings and product: +15°C-25°C. Do not apply below +10°C. Ideal surface and object temperature for application: +18°C-22°C. Avoid application in direct sunlight. Underfloor heating systems must be adjusted well in advance.

**Drying time** +23°C / 65% RH  
- dust free after 2 (2-3) hours  
- overcoatable after 6-8 (16) hours  
- fit for sanding after 2 hours  
- through dry after 7 days

**Cleaning** Wash the equipment immediately after use. TERPENTINERSATZ 4214-98

## HEALTH AND SAFETY

<b>Safety and precaution measures</b>	See safety data sheet.
<b>First aid</b>	We recommend wearing personal protective clothing even in cases where no local regulations are in force. CH: The precautions according to local regulations (SUVA) with respect to hygiene and equipment must be observed.

## ADDITIONAL INFORMATION

<b>Maintenance instructions</b>	Parquet floors: Maintenance: After at least 3 weeks curing time with RENSA WOOD OIL POLISH 4584-00. Re-impregnate with RENSA WOOD CARE OIL 1413. Carpenter application: Maintenance: After a minimum period of 3 weeks by wiping surfaces with a damp cloth (not wet). As required, e.g. weekly, add approx. 1% RENSA WOOD OIL POLISH 4584-00 to the cleaning water (2 caps to 1l of water). Cleans and nourishes the oiled surface. Re-impregnate with RENSA WOOD CARE OIL 1413.  For further information on products for treating the surfaces of wooden floors and their use please visit <a href="http://www.parkett-verband.ch">www.parkett-verband.ch</a>
---------------------------------	--

**Teknos Group Oy Takkatie 3, P.O.Box 107 FI-00371 Helsinki, Finland Tel. +358 9 506 091**

The above information is normative and based on laboratory tests and practical experiences. The information is noncommittal, and we cannot accept liability for the results obtained under working conditions beyond our control, and consequently the buyer or the user is not released from the obligation to test the suitability of our products for specific means and application methods under the actual application conditions. Our liability covers only damage caused directly by defects in the products supplied by Teknos. This product is intended for professional use only. This implies that the user possesses sufficient knowledge for using the product correctly with regard to technical and working safety aspects. The latest versions of Teknos' Technical Data Sheets and Safety Data Sheets are available from our homepage [www.teknos.com](http://www.teknos.com). All trademarks displayed on this document are the exclusive property of Teknos Group or its affiliated companies.