

# **OW COMBI 2315-60**

Solvent-based, grain-accentuating 1C primer and top coat for interior use

OW COMBI 2315 is a fast-drying, solvent-based, grain-accentuating 1C primer and top coat which feels pleasant to the touch. The chemical and mechanical strength can be improved by adding hardeners.





## **TECHNICAL DATA**

Fields of application	Furniture
Binder	Alkyd
Solids	Approx. 23% by weight
Volatile organic compound (VOC)	Approx. 712 g/l (DIRECTIVE 2010/75/EU)
	The VOC value provided is the average value for factory produced products, and consequently it will be subject to variations between individual products covered by this Technical Data Sheet.
Theoretical spreading rate	100 g/m²; 10 m²/kg
Colours	Colourless.
Tinting system	Largo
Gloss (60°)	60
Thinner	OWEDUR 3502-98
Density	Approx. 0.92 g/ml
Storage	Storage temperature is +5°C - +30°C.

### **DIRECTION FOR USE**

Surface preparation	Every substrate must be well-cleaned, dry and free from grease and oil. Coating
	removal: Sand, strip
Application method	Conventional spraying, Airless spraying, Air-assisted airless spraying



Application	Stir or shake the product well for several minutes before use, if necessary by machine.								
	APPLICATION ADVICE								
	Wood substrate raw								
		Product			Applied Quantity				
	Presanding	With grain 150-180							
	Primer	OW COMBI 2315			80-120 g/m²				
	Intermediate sanding	With grain 280-400							
	Recoating	OW COMBI 2316			80-120 g/m²				
	For further application proposals please ask our representative.								
		APPLICATION							
		Viscosity DIN 4 mm	Dilution	Nozzle in mm	Pressure in bar	Spray Cycles			
	Gravity Feed Gun	18-22"	15-30%	1.4-1.8	2-3	1-2			
	Airless / Airmix Spray Application	30-33"	undiluted	0.15-0.23	Material 60-80	1-2			
	Pouring	28-30"	10%						
Application conditions	Recommende	d temperatu	re for surrour	ndings and pro	oduct: +15°C-	25°C. Do not			
	apply below +10°C.								
Drying time	+23°C / 50% RH (dry film 20 μm)								
- dust free	after 10 minutes								
- touch dry	after 60 minutes								
- overcoatable	after 3 hours								
- fit for sanding	after 3 hours								
- through dry	after 14 hours								
Cleaning	Wash the equipment immediately after use. OWEDUR 3502-98								

### **HEALTH AND SAFETY**

Safety and precaution measures

See safety data sheet.

#### Teknos Group Oy Takkatie 3, P.O.Box 107 FI-00371 Helsinki, Finland Tel. +358 9 506 091

The above information is normative and based on laboratory tests and practical experiences. The information is noncommittal, and we cannot accept liability for the results obtained under working conditions beyond our control, and consequently the buyer or the user is not released from the obligation to test the suitability of our products for specific means and application methods under the actual application conditions. Our liability covers only damage caused directly by defects in the products supplied by Teknos. This product is intended for professional use only. This implies that the user possesses sufficient knowledge for using the product correctly with regard to technical and working safety aspects. The latest versions of Teknos' Technical Data Sheets and Safety Data Sheets are available from our homepage www.teknos.com. All trademarks displayed on this document are the exclusive property of Teknos Group or its affiliated companies.