

PFLEGESPRAYÖL 1413-25

Solvent-based, high-quality maintenance preservative oil for interior use

RENSA WOOD CARE OIL1413 is a high-quality, low-viscosity preservative care oil for the maintenance of parquet floors treated with oxidative and UV oil as well as for the final oil application on wooden floors that have been pre-treated with oxidative oil at the works. The product is easy to use and dries quickly.



Information on contained substances (according to EU recommendations): Natural linseed oil/stand oil mixture, odourless turpentine substitute.

TECHNICAL DATA

Fields of application	Furniture, Floors
Solids	Approx. 17% by weight
Volatile organic compound (VOC)	Approx. 684 g/l (DIRECTIVE 2010/75/EU)
	The VOC value provided is the average value for factory produced products, and
	consequently it will be subject to variations between individual products
	covered by this Technical Data Sheet.
Theoretical spreading rate	25 g/m²; 40 m²/kg
Colours	Colourless. White. Black. Can be adjusted individually for customers by
	agreement.
Density	Approx. 0.8 g/ml
Storage	Storage temperature is +5°C - +30°C. Store in a tightly closed container.

DIRECTION FOR USE

Surface preparation	Every substrate must be well-cleaned, dry and free from grease and oil.
Application method	Cloth, Smooth roller
	Hazard warning:
	Pads and cloths soaked in oil can spontaneously combust under certain
	circumstances and should therefore be kept in a metal bin with a lid until they
	are disposed of.

PFLEGESPRAYÖL 1413-25



Application	Stir or shake the product well for several minutes before use, if necessary by		
	machine.		
	APPLICATION ADVICE		
	Oiled floors		
		Product	Applied Quantity
	Care	RENSA WOOD CARE OIL 1413	25-50 g/m²
		Massage in with beige pad (tan) (art. no. N948103); repeat process if necessary.	
	Fo	r further application proposals please ask our representat	ive.
Application conditions	Recommended temperature for surroundings and product: +15°C-25°C. Do not		
	apply below +10°C. Ideal surface and object temperature for application:		
	+18°C-22°C. Avoid application in direct sunlight. Underfloor heating systems		
	must be adjusted v	vell in advance.	
Drying time	+23°C / 50% RH (d	ry film 20 μm)	
- dust free	after 60 minutes		
- touch dry	after 2 hours		
- through dry	after 7 days		
Cleaning	Wash the equipme	nt immediately after use. TERPENTINERS	ATZ 4214-98

HEALTH AND SAFETY

Safety and precaution measures	See safety data sheet.
First aid	We recommend wearing personal protective clothing even in cases where no
	local regulations are in force.
	CH: The precautions according to local regulations (SUVA) with respect to
	hygiene and equipment must be observed.

ADDITIONAL INFORMATION

Maintenance instructions

Lightly sand the wood to be subsequently treated with a green or beige pad and clean well. Use a dispenser to apply a fine spray coat. Use a single-disc machine and beige pad to work the product in. Dust dry after about one hour.

Regular maintenance with RENSA WOOD OIL POLISH 4584-00 for the first time after at least seven days curing time (refer to data sheet N4584).

Also refer to our brochure "Perfect parquet floor care".

For further information on products for treating the surfaces of wooden floors and their use please visit www.parkett-verband.ch.



Teknos Group Oy Takkatie 3, P.O.Box 107 FI-00371 Helsinki, Finland Tel. +358 9 506 091

The above information is normative and based on laboratory tests and practical experiences. The information is noncommittal, and we cannot accept liability for the results obtained under working conditions beyond our control, and consequently the buyer or the user is not released from the obligation to test the suitability of our products for specific means and application methods under the actual application conditions. Our liability covers only damage caused directly by defects in the products supplied by Teknos. This product is intended for professional use only. This implies that the user possesses sufficient knowledge for using the product correctly with regard to technical and working safety aspects. The latest versions of Teknos' Technical Data Sheets and Safety Data Sheets are available from our homepage www.teknos.com. All trademarks displayed on this document are the exclusive property of Teknos Group or its affiliated companies.