

RENO GRUND NORDIC 3338-00

Lightening 1C alcohol-based parquet primer

RENO GRUND NORDIC 3338-00 is a lightening, alcohol-based parquet primer with slight, permanent UV protection. The coating is suitable in the renovation sector for isolating stain-forming substances from the wood substrate and is mainly used on light woods. RENO GRUND NORDIC 3338-00 reduces the tendency to side edge bonding and therefore lowers the risk of the formation of wide joint cracks (block cracks).



TECHNICAL DATA

Certificates, approvals and classification	Swiss environmental label UE II, class F
Fields of application	Floors
Solids	Approx. 11% by weight
Volatile organic compound (VOC)	Approx. 702 g/l (DIRECTIVE 2010/75/EU) The VOC value provided is the average value for factory produced products, and consequently it will be subject to variations between individual products covered by this Technical Data Sheet.
Theoretical spreading rate	125 g/m ² ; 8 m ² /kg
Colours	Colourless.
Tinting system	Largo
Density	Approx. 0.84 g/ml
Storage	Storage temperature is +5°C - +30°C. Store in a tightly closed container.

DIRECTION FOR USE

Surface preparation	Every substrate must be well-cleaned, dry and free from grease and oil. Coating removal: Sand
Application method	Brush, Roller When using RENO GRUND NORDIC 3338-00 as a primer, always use a separate roller.

Application

Stir or shake the product well for several minutes before use, if necessary by machine.

APPLICATION ADVICE		
Raw parquet flooring		
	Product	Applied Quantity
Primer	RENO GRUND NORDIC 3338	125 g/m ²
Recoating	Parkettsiegel	120 g/m ²
Intermediate sanding		
Recoating	Parkettsiegel	120 g/m ²
For further application proposals please ask our representative.		

Application conditions

Recommended temperature for surroundings and product: +15°C–25°C. Do not apply below +10°C. Ideal surface and object temperature for application: +18°C–22°C. Avoid application in direct sunlight. Underfloor heating systems must be adjusted well in advance.

Drying time

+23°C / 65% RH

- dust free

after 60 minutes

- overcoatable

after 3 hours

Cleaning

Wash the equipment immediately after use. VERDÜNNER 1000-98 or POLITURSPRIT 4100-98.

HEALTH AND SAFETY

Safety and precaution measures

See safety data sheet. Do not smoke during the application and keep away from ignition sources.

First aid

We recommend wearing personal protective clothing even in cases where no local regulations are in force.

CH: The precautions according to local regulations (SUVA) with respect to hygiene and equipment must be observed.

ADDITIONAL INFORMATION

Maintenance instructions

For further information on products for treating the surfaces of wooden floors and their use please visit www.parkett-verband.ch.

Teknos Group Oy Takkatie 3, P.O.Box 107 FI-00371 Helsinki, Finland Tel. +358 9 506 091

The above information is normative and based on laboratory tests and practical experiences. The information is noncommittal, and we cannot accept liability for the results obtained under working conditions beyond our control, and consequently the buyer or the user is not released from the obligation to test the suitability of our products for specific means and application methods under the actual application conditions. Our liability covers only damage caused directly by defects in the products supplied by Teknos. This product is intended for professional use only. This implies that the user possesses sufficient knowledge for using the product correctly with regard to technical and working safety aspects. The latest versions of Teknos' Technical Data Sheets and Safety Data Sheets are available from our homepage www.teknos.com. All trademarks displayed on this document are the exclusive property of Teknos Group or its affiliated companies.