

RENSA FLOOR POLISH 4580-15

Polymer dispersion for the care and maintenance of all parquet and cork floors with a water-resistant finish

RENSA FLOOR POLISH 4580 is a polymer dispersion for the care and maintenance of all parquet and cork floors with a water-resistant finish. Maintains and protects old floors, restoring their (satin) matt or matt finish. Enhances the natural grain of the floor and intensifies its colour.

TECHNICAL DATA

Solids	Approx. 100% by weight
Volatile organic compound (VOC)	Approx. 0 g/l (DIRECTIVE 2010/75/EU)
	The VOC value provided is the average value for factory produced products, and
	consequently it will be subject to variations between individual products
	covered by this Technical Data Sheet.
Theoretical spreading rate	25 g/m²; 40 m²/kg
Colours	Colourless.
Gloss (60°)	15
Density	Approx. 1.02 g/ml
Storage	Storage temperature is +5°C - +30°C. Store in a tightly closed container.

Surface preparation	Every substrate r	Every substrate must be well-cleaned, dry and free from grease and oil.			
Application	Stir or shake the	Stir or shake the product well for several minutes before use, if necessary by			
	machine.	machine.			
		APPLICATION ADVICE			
	Water-resistant finish	Water-resistant finished parquet and cork floors			
		Product	Applied Quantity		
	Care	RENSA FLOOR POLISH 4580	25 g/m²		
	UV-sealed finished par	UV-sealed finished parquet			
		Product	Applied Quantity		
	Care	RENSA FLOOR POLISH 4580	25 g/m²		
		For further application proposals please ask our representative.			
Application conditions	Recommended to	emperature for surroundings and produc	t: +15°C-25°C. Do not		
	apply below +10	°C. Ideal surface and object temperature	for application:		
	+18°C-22°C. Av	oid application in direct sunlight. Underflo	oor heating systems		

must be adjusted well in advance.

RENSA FLOOR POLISH 4580-15



Drying time +23°C / 50% RH (dry film 20 μ m)

dust free after 40 minutes
touch dry after 3 hours
overcoatable after 1 day
through dry after 6 days

Cleaning Wash the equipment immediately after use.

HEALTH AND SAFETY

Safety and precaution measures	See safety data sheet.	
First aid	We recommend wearing personal protective clothing even in cases where no	
	local regulations are in force.	
	CH: The precautions according to local regulations (SUVA) with respect to	
	hygiene and equipment must be observed.	

ADDITIONAL INFORMATION

Maintenance instructions Inistial care: Wait for at least 3 weeks before thoroughly cleaning hardwood

floors. If the floor is very dirty, use RENSA PRO CLEAN 4582-00 as a pre-

treatment.

Let dry for at least 12h, ideally overnight.

Maintenance: Remove dirt and dust with a vacuum and/or by mopping. Add 1 part of FLOOR POLISH 4580 to 5 I of cleaning water (equivalent to 2%).

Also refer to our brochure "Perfect parquet floor care".

For further information on products for treating the surfaces of wooden floors and their use please visit www.parkett-verband.ch.

Teknos Group Oy Takkatie 3, P.O.Box 107 FI-00371 Helsinki, Finland Tel. +358 9 506 091

The above information is normative and based on laboratory tests and practical experiences. The information is noncommittal, and we cannot accept liability for the results obtained under working conditions beyond our control, and consequently the buyer or the user is not released from the obligation to test the suitability of our products for specific means and application methods under the actual application conditions. Our liability covers only damage caused directly by defects in the products supplied by Teknos. This product is intended for professional use only. This implies that the user possesses sufficient knowledge for using the product correctly with regard to technical and working safety aspects. The latest versions of Teknos' Technical Data Sheets and Safety Data Sheets are available from our homepage www.teknos.com. All trademarks displayed on this document are the exclusive property of Teknos Group or its affiliated companies.