

RENSA FLOOR POLISH 4580-30

Polymer dispersion for the care and maintenance of all parquet and cork floors with a water-resistant finish

RENSA FLOOR POLISH 4580 is a polymer dispersion for the care and maintenance of all parquet and cork floors with a water-resistant finish.

Maintains and protects old floors, restoring their (satin) matt or matt finish.

Enhances the natural grain of the floor and intensifies its colour.

pH value: approx. 8.5 (concentrate)

Information on contained substances (according to EU recommendations):

Less than 5 % non-ionic surfactants. Additional ingredients: Care ingredients, auxiliaries and fragrances.



TECHNICAL DATA

Fields of application	Floors		
Solids	Approx. 50% by weight		
Theoretical spreading rate	25 g/m²; 40 m²/kg		
Colours	Colourless.		
Gloss (60°)	30		
Density	Approx. 1.01 g/ml		
Storage	Storage temperature is +5°C - +30°C. Store in a tightly closed container.		

DIRECTION FOR USE

Every substrate i	Every substrate must be well-cleaned, dry and free from grease and oil.		
Cloth, Smooth ro	Cloth, Smooth roller		
Shake or stir pro	Shake or stir product well before use.		
	APPLICATION ADVICE		
Water-resistant finish	Water-resistant finished parquet and cork floors		
	Product	Applied Quantity	
Care	RENSA FLOOR POLISH 4580	25 g/m²	
UV-sealed finished par	UV-sealed finished parquet		
	Product	Applied Quantity	
Care	RENSA FLOOR POLISH 4580	25 g/m²	
	For further application proposals please ask our representative.		
	Cloth, Smooth ro Shake or stir prod Water-resistant finish Care UV-sealed finished par	Cloth, Smooth roller Shake or stir product well before use. APPLICATION ADVICE Water-resistant finished parquet and cork floors Product Care RENSA FLOOR POLISH 4580 UV-sealed finished parquet Product RENSA FLOOR POLISH 4580	

Application conditions

Recommended temperature for surroundings and product: +15°C-25°C. Do not apply below +10°C. Ideal surface and object temperature for application: +18°C-22°C. Avoid application in direct sunlight. Underfloor heating systems must be adjusted well in advance.

RENSA FLOOR POLISH 4580-30



Drying time +23°C / 50% RH (dry film 20 μ m)

dust free after 40 minutes
 touch dry after 3 hours
 overcoatable after 1 day
 through dry after 6 days

Can be walked on after initial care: After 6 hours. Can be walked on after maintenance: After 2 hrs.

Cleaning Wash the equipment immediately after use.

HEALTH AND SAFETY

Safety and precaution measures See safety data sheet.

ADDITIONAL INFORMATION

Maintenance instructions Inistial care: Wait for at least 3 weeks before thoroughly cleaning hardwood

floors. If the floor is very dirty, use RENSA PRO CLEAN 4582-00 as a pre-

treatment.

Let dry for at least 12h, ideally overnight.

Maintenance: Remove dirt and dust with a vacuum and/or by mopping. Add 1 part of FLOOR POLISH 4580 to 5 I of cleaning water (equivalent to 2%).

Also refer to our brochure "Perfect parquet floor care".

For further information on products for treating the surfaces of wooden floors

and their use please visit www.parkett-verband.ch.

Teknos Group Oy Takkatie 3, P.O.Box 107 Fl-00371 Helsinki, Finland Tel. +358 9 506 091

The above information is normative and based on laboratory tests and practical experiences. The information is noncommittal, and we cannot accept liability for the results obtained under working conditions beyond our control, and consequently the buyer or the user is not released from the obligation to test the suitability of our products for specific means and application methods under the actual application conditions. Our liability covers only damage caused directly by defects in the products supplied by Teknos. This product is intended for professional use only. This implies that the user possesses sufficient knowledge for using the product correctly with regard to technical and working safety aspects. The latest versions of Teknos' Technical Data Sheets and Safety Data Sheets are available from our homepage www.teknos.com. All trademarks displayed on this document are the exclusive property of Teknos Group or its affiliated companies.