

ROCKFLOOR 6500-15

Solvent-based 2C PU sealing coating for anhydrite and cement floors for interior use



ROCKFLOOR 6500 is a solvent-based 2C PU sealing coating with excellent resistance and is exceptionally fast-drying for high quality, transparent sealing of anhydrite and cement floors. The product is resistant to light and yellowing.



TECHNICAL DATA

Certificates, approvals and classification	Swiss environmental label UE II, class G
Fields of application	Floors
Binder	Acrylate
Solids	Approx. 32% by weight
Volatile organic compound (VOC)	Approx. 689 g/l (DIRECTIVE 2010/75/EU) The VOC value provided is the average value for factory produced products, and consequently it will be subject to variations between individual products covered by this Technical Data Sheet.
Theoretical spreading rate	200 g/m ² ; 5 m ² /kg
Colours	Colourless. Can be adjusted individually for customers by agreement.
Tinting system	Largo
Gloss (60°)	15
Hardener	Mix in hardener mechanically for several minutes. Comp. B: ROCKFLOOR 6500-99
Mixing ratio (A:B)	10:1 parts by volume
Pot life, +23°C	24 h
Thinner	VERDÜNNER 1300-98, VERDÜNNER 5500-98.
Density	Approx. 0.96 g/ml
Storage	Storage temperature is +5°C - +30°C.

DIRECTION FOR USE

Surface preparation	Every substrate must be well-cleaned, dry and free from grease and oil. Coating removal: Sand
Application method	Brush, Roller

Application

Stir or shake the product well for several minutes before use, if necessary by machine.

APPLICATION ADVICE		
Anhydrite or cement underlay floors		
	Product	Applied Quantity
Sanding	With grain 100-120 then dust off well with an industrial Hoover	
Primer	ROCKFLOOR 6500	200 - 400 g/m ²
	1. Coating with 10 mm Polytex roll	
Recoating	ROCKFLOOR 6500	120 - 180 g/m ²
	2. Coating 4-10 mm roller	
Intermediate sanding	with grain 150 / green pad (sia)	
Recoating	ROCKFLOOR 6500	100 - 120 g/m ²
	3. Coating 4-10 mm roller	
For further application proposals please ask our representative.		

Application conditions

Recommended temperature for surroundings and product: +15°C-25°C. Do not apply below +10°C. Ideal surface and object temperature for application: +18°C-22°C. Avoid application in direct sunlight. Underfloor heating systems must be adjusted well in advance.

Drying time

+23°C / 50% RH (dry film 20 µm)

- dust free

after 60 minutes

- overcoatable

after 8 hours or wet in wet application

- fit for sanding

after 8 hours

- through dry

after 7 days

Cleaning

Wash the equipment immediately after use. VERDÜNNER 1000-98, VERDÜNNER 1300-98, VERDÜNNER 5500-98.

HEALTH AND SAFETY

Safety and precaution measures

See safety data sheet.

ADDITIONAL INFORMATION

Maintenance instructions

Initial and maintenance care: After at least 3 weeks curing time with RENSA FLOOR POLISH 4580

For more information on wood floor surface treatments and their use, visit www.parkett-verband.ch.

Teknos Group Oy Takkatie 3, P.O.Box 107 FI-00371 Helsinki, Finland Tel. +358 9 506 091

The above information is normative and based on laboratory tests and practical experiences. The information is noncommittal, and we cannot accept liability for the results obtained under working conditions beyond our control, and consequently the buyer or the user is not released from the obligation to test the suitability of our products for specific means and application methods under the actual application conditions. Our liability covers only damage caused directly by defects in the products supplied by Teknos. This product is intended for professional use only. This implies that the user possesses sufficient knowledge for using the product correctly with regard to technical and working safety aspects. The latest versions of Teknos' Technical Data Sheets and Safety Data Sheets are available from our homepage www.teknos.com. All trademarks displayed on this document are the exclusive property of Teknos Group or its affiliated companies.