

# SCAN FINISH 0849-25

## Acid-curing 1C top coat

SCAN FINISH 0849 is an acid-curing single-component coating.



### TECHNICAL DATA

<b>Solids</b>	Approx. 27% by weight
<b>Volatile organic compound (VOC)</b>	Approx. 682 g/l (DIRECTIVE 2010/75/EU) The VOC value provided is the average value for factory produced products, and consequently it will be subject to variations between individual products covered by this Technical Data Sheet.
<b>Colours</b>	Colourless.
<b>Gloss (60°)</b>	25
<b>Density</b>	Approx. 0.94 g/ml
<b>Storage</b>	Storage temperature is +5°C - +30°C.

### DIRECTION FOR USE

<b>Surface preparation</b>	Every substrate must be well-cleaned, dry and free from grease and oil. Coating removal: Sand, strip
<b>Application</b>	Stir or shake the product well for several minutes before use, if necessary by machine.
<b>Application conditions</b>	Recommended temperature for surroundings and product: +15°C-25°C. Do not apply below +10°C.
<b>Drying time</b>	+23°C / 50% RH (dry film 20 µm)
<b>Cleaning</b>	Wash the equipment immediately after use. VERDÜNNER 1300-98 or VERDÜNNER 0950-98.

### HEALTH AND SAFETY

<b>Safety and precaution measures</b>	See safety data sheet.
---------------------------------------	------------------------

**Teknos Group Oy Takkatie 3, P.O.Box 107 FI-00371 Helsinki, Finland Tel. +358 9 506 091**

The above information is normative and based on laboratory tests and practical experiences. The information is noncommittal, and we cannot accept liability for the results obtained under working conditions beyond our control, and consequently the buyer or the user is not released from the obligation to test the suitability of our products for specific means and application methods under the actual application conditions. Our liability covers only damage caused directly by defects in the products supplied by Teknos. This product is intended for professional use only. This implies that the user possesses sufficient knowledge for using the product correctly with regard to technical and working safety aspects. The latest versions of Teknos' Technical Data Sheets and Safety Data Sheets are available from our homepage [www.teknos.com](http://www.teknos.com). All trademarks displayed on this document are the exclusive property of Teknos Group or its affiliated companies.