

# **SPRITZSPACHTEL 0841-00**

# Solvent-based 1C spray filler for interior use

SPRITZSPACHTEL 0841-00 is a solvent-based 1C spray filler with good filling properties and sandability. The coating is ideal for wetrooms due to its isolating effect.





## **TECHNICAL DATA**

Fields of application	Furniture, Fixed furniture, Interior doors
Binder	Alkyd
Solids	Approx. 51% by weight
Theoretical spreading rate	175 g/m²; 5.7 m²/kg
Colours	White.
Thinner	VERDÜNNER 1000-98
Density	Approx. 1.25 g/ml
Storage	Storage temperature is +5°C - +30°C. Store in a tightly closed container.

### **DIRECTION FOR USE**

Surface preparation	Every substrate must be well-cleaned, dry and free from grease and oil. Coating
	removal: Sand, strip
Application method	Conventional spraying, Airless spraying, Air-assisted airless spraying



#### Application

Stir or shake the product well for several minutes before use, if necessary by machine.

	machine.						
	APPLICATION ADVICE Wood substrate						
			Product		Applied Quantity		
	Presanding	SPR	RITZSPACHTEL 84	ZSPACHTEL 841SP		150-200 g/m²	
	Primer	V	Vith grain 180-22	0			
	Intermediate sanding	SPR	RITZSPACHTEL 84	1SP 150-200 g/r		00 g/m²	
	Recoating	Colou	ur lacquer of your choice				
	MDF/HDF raw						
			Product		Applied Quantity		
	Primer	SPRITZSPACHTEL 841SP		1SP	150-180 g/m²		
	Intermediate sanding	V	With grain 180-240 SPRITZSPACHTEL 841SP				
	Primer	-			150-200 g/m²		
	Recoating						
	For further application proposals please ask our representative. APPLICATION						
		Viscosity DIN 4 mm	Dilution	Nozzle in mm	Pressure in bar	Spray Cycles	
	Gravity Feed Gun	25-30"	10-15%	1.8-2.5	3-4	1-2	
	Suction Cup Gun	25-30"	10-15%	1.8-2.5	3-4	1-2	
	Airless / Airmix Spray Application	30-40"	5-10%	0.28-0.33		1-2	
	HVLP-Pistol	25-30"	15%	1.8-2.5	3-4	1-2	
Application conditions	Recommended temperature for surroundings and product: +15°C-25°C. Do no			25°C. Do not			
	apply below +10°C.						
Drying time	+23°C / 65% RH						
- dust free	after 60 minutes						
- touch dry	after 50 minutes						
- overcoatable	after 8 hours						
- fit for sanding	after 5-6 hours						
- through dry	after 10 hours						
	Wash the equipment immediately after use. VERDÜNNER 1000-98						
Cleaning	wash the equi	pinent imme	ulately after	USE. VERDUN	NEK 1000-98	j	

#### **HEALTH AND SAFETY**

Safety and precaution measures	See safety data sheet.
First aid	We recommend wearing personal protective clothing even in cases where no local regulations are in force.

CH: The precautions according to local regulations (SUVA) with respect to hygiene and equipment must be observed.



#### Teknos Group Oy Takkatie 3, P.O.Box 107 FI-00371 Helsinki, Finland Tel. +358 9 506 091

The above information is normative and based on laboratory tests and practical experiences. The information is noncommittal, and we cannot accept liability for the results obtained under working conditions beyond our control, and consequently the buyer or the user is not released from the obligation to test the suitability of our products for specific means and application methods under the actual application conditions. Our liability covers only damage caused directly by defects in the products supplied by Teknos. This product is intended for professional use only. This implies that the user possesses sufficient knowledge for using the product correctly with regard to technical and working safety aspects. The latest versions of Teknos' Technical Data Sheets and Safety Data Sheets are available from our homepage www.teknos.com. All trademarks displayed on this document are the exclusive property of Teknos Group or its affiliated companies.