

UNIVERSALPRIMER 0216-00

Solvent-based 1C shop-primer for interior and exterior use

UNIVERSALPRIMER 0216-00 is a solvent-based 1C shop primer for various metal substrates with active corrosion protection.



TECHNICAL DATA

Solids	Approx. 45% by weight
Theoretical spreading rate	50-100; 7.8 m ² /kg
Thinner	VERDÜNNER 1000-98
Density	Approx. 1.168 g/ml
Storage	Storage temperature is +5°C - +30°C. Store in a tightly closed container.

DIRECTION FOR USE

Surface preparation	Every substrate must be well-cleaned, dry and free from grease and oil. Coating removal: Sand, sandblast
Application method	Conventional spraying, Airless spraying, Air-assisted airless spraying Shop-primer, generally universally suitable for subsequent air and oven-curing coatings. Coated surfaces can be welded. Weldability is based on practical experience, depends on the substrate and the applied layer thickness. Appropriate suitability tests must be carried out before use.
Application	Stir or shake the product well for several minutes before use, if necessary by machine.
Application conditions	Recommended temperature for surroundings and product: +15°C-25°C. Do not apply below +10°C.
Drying time	+23°C / 65% RH
- overcoatable	after 30-45 minutes
Cleaning	Wash the equipment immediately after use. VERDÜNNER 1000-98 or UNIVERSALREINIGER U 8600-98.

HEALTH AND SAFETY

Safety and precaution measures	See safety data sheet.
---------------------------------------	------------------------

First aid

We recommend wearing personal protective clothing even in cases where no local regulations are in force.

CH: The precautions according to local regulations (SUVA) with respect to hygiene and equipment must be observed.

Teknos Group Oy Takkatie 3, P.O.Box 107 FI-00371 Helsinki, Finland Tel. +358 9 506 091

The above information is normative and based on laboratory tests and practical experiences. The information is noncommittal, and we cannot accept liability for the results obtained under working conditions beyond our control, and consequently the buyer or the user is not released from the obligation to test the suitability of our products for specific means and application methods under the actual application conditions. Our liability covers only damage caused directly by defects in the products supplied by Teknos. This product is intended for professional use only. This implies that the user possesses sufficient knowledge for using the product correctly with regard to technical and working safety aspects. The latest versions of Teknos' Technical Data Sheets and Safety Data Sheets are available from our homepage www.teknos.com. All trademarks displayed on this document are the exclusive property of Teknos Group or its affiliated companies.