

VARIVA AQUA 8770-00 WIPE

Water-soluble wipe stain

VARIVA AQUA 8770-00 WIPE wipe stain is a water-borne, ready-to-use, light-fast pigment stain that creates a rustic stain effect on coarse-pored woods such as oak and ash. VARIVA AQUA 8770-00 WIPE provides a pore-accentuating and rustic stain effect in wood shades and can also be used on fine-pored woods such as maple.



TECHNICAL DATA

Fields of application	Bathroom, Furniture, Kitchen, Kitchen furniture, Panels, Stairs, Mouldings, Interior doors, Boards
Binder	Polyurethane
Solids	Approx. 7% by weight
Volatile organic compound (VOC)	Approx. 78 g/l (DIRECTIVE 2010/75/EU) The VOC value provided is the average value for factory produced products, and consequently it will be subject to variations between individual products covered by this Technical Data Sheet.
Colours	Can be adjusted individually for customers by agreement.
Tinting system	Largo
Density	Approx. 1.01 g/ml
Storage	Storage temperature is +5°C - +30°C.

DIRECTION FOR USE

Surface preparation	Every substrate must be well-cleaned, dry and free from grease and oil. Coating removal: Sand, strip
Application method	Conventional spraying, HVLP spraying, Sponge Before commencing work always test the product on the original wood. The shade depends on several factors such as the wood characteristics, wood shade, sanded finish etc.

Stains must always be fixed and protected with at least one coat of a clear coating. No intermediate sanding should be carried out before priming. The final colour shades are only obtained after priming, intermediate sanding and final coating with a clear coating and after drying at least overnight.

Application	Stir or shake the product well for several minutes before use, if necessary by machine.			
	APPLICATION ADVICE			
	Wood substrate raw			
		Product	Applied Quantity	
	Presanding	With grain 150, then 180 (Follow correct order)		
	Stain	VARIVA AQUA 8770 WIPE	1x generously	
	Recoating	Varnish	120-150 g/m ²	
	Intermediate sanding	With grain 220-280		
	Recoating	Varnish	120-150 g/m ²	
	For further application proposals please ask our representative.			
APPLICATION				
	Viscosity	Dilution	Nozzle in mm	Pressure in bar
Gravity Feed Gun	Delivery viscosity	undiluted	1.2-1.4	0.8-1 bar

Application conditions Recommended temperature for surroundings and product: +15°C-25°C. Do not apply below +10°C.

Drying time	+23°C / 50% RH (dry film 20 µm)
- dust free	after 60 minutes
- touch dry	after 60 minutes
- overcoatable	after 12-24 hours
	Reworkability for veneered surfaces after 12 hours, for solid wood after 24 hours at 20°C and 65% relative humidity

Cleaning Wash the equipment immediately after use. Water, ACETON 8000-98.

HEALTH AND SAFETY

Safety and precaution measures See safety data sheet.

Teknos Group Oy Takkatie 3, P.O.Box 107 FI-00371 Helsinki, Finland Tel. +358 9 506 091

The above information is normative and based on laboratory tests and practical experiences. The information is noncommittal, and we cannot accept liability for the results obtained under working conditions beyond our control, and consequently the buyer or the user is not released from the obligation to test the suitability of our products for specific means and application methods under the actual application conditions. Our liability covers only damage caused directly by defects in the products supplied by Teknos. This product is intended for professional use only. This implies that the user possesses sufficient knowledge for using the product correctly with regard to technical and working safety aspects. The latest versions of Teknos' Technical Data Sheets and Safety Data Sheets are available from our homepage www.teknos.com. All trademarks displayed on this document are the exclusive property of Teknos Group or its affiliated companies.