

VARIVA PLUS 8779-00

Water-borne single positive stain

VARIVA PLUS 8779-00 spray stain is a water-borne, ready-to-use, single positive stain that has a particularly positive stain effect on softwood or hardwood furniture. VARIVA PLUS 8779-00 creates an attractive and elegant stained surface, especially on beech, which is difficult to stain. VARIVA PLUS 8779-00 produces an even and appealing stain on all furniture, panelling and interiors.



TECHNICAL DATA

Fields of application	Bathroom, Furniture, Kitchen, Kitchen furniture, Panels, Stairs, Mouldings, Interior doors, Boards
Solids	Approx. 1% by weight
Volatile organic compound (VOC)	Approx. 33 g/l (DIRECTIVE 2010/75/EU) The VOC value provided is the average value for factory produced products, and consequently it will be subject to variations between individual products covered by this Technical Data Sheet.
Colours	Can be adjusted individually for customers by agreement.
Tinting system	Largo
Density	Approx. 1.02 g/ml
Storage	Storage temperature is +5°C - +30°C.

DIRECTION FOR USE

Surface preparation	Every substrate must be well-cleaned, dry and free from grease and oil. Coating removal: Sand, strip
----------------------------	--

Application method

Conventional spraying, HVLP spraying, Sponge, Brush

Before commencing work always test the product on the original wood. The shade depends on several factors such as the wood characteristics, wood shade, sanded finish etc. Spongy and irregular woods as well as end grain should be treated with BEIZAUSGLEICH 0634-00 beforehand. Apply BEIZAUSGLEICH 0634-00 liberally, do not remove excess, allow to dry, do not sand.

Stains must always be fixed and protected with at least one coat of a clear coating. No intermediate sanding should be carried out before priming. The final colour shades are only obtained after priming, intermediate sanding and final coating with a clear coating and after drying at least overnight.

Application

Stir or shake the product well for several minutes before use, if necessary by machine.

APPLICATION ADVICE					
Wood substrate raw					
	Product			Applied Quantity	
Presanding	Soft wood with grain 100 Hard wood with grain 180				
Stain	VARIVA PLUS 8779			45-50 g/m ²	
Recoating	Varnish			100-120 g/m ²	
Intermediate sanding	With grain 220-280				
Recoating	Varnish			100-120 g/m ²	
For further application proposals please ask our representative.					
APPLICATION					
	Viscosity	Dilution	Nozzle in mm	Pressure in bar	Spray Cycles
Gravity Feed Gun	Delivery viscosity	undiluted	1.2-1.4	0.8-1	1

Application conditions

Recommended temperature for surroundings and product: +15°C–25°C. Do not apply below +10°C.

Drying time

+23°C / 50% RH (dry film 20 µm)

- dust free

after 60 minutes

- touch dry

after 60 minutes

- overcoatable

after 4-5 hours

Veneered surfaces can be reworked after 4-5 hours, solid wood after 24 hours at 20°C and 65% relative humidity

Cleaning

Wash the equipment immediately after use. Water, ACETON 8000-98.

HEALTH AND SAFETY

Safety and precaution measures

See safety data sheet.

Teknos Group Oy Takkatie 3, P.O.Box 107 FI-00371 Helsinki, Finland Tel. +358 9 506 091

The above information is normative and based on laboratory tests and practical experiences. The information is noncommittal, and we cannot accept liability for the results obtained under working conditions beyond our control, and consequently the buyer or the user is not released from the obligation to test the suitability of our products for specific means and application methods under the actual application conditions. Our liability covers only damage caused directly by defects in the products supplied by Teknos. This product is intended for professional use only. This implies that the user possesses sufficient knowledge for using the product correctly with regard to technical and working safety aspects. The latest versions of Teknos' Technical Data Sheets and Safety Data Sheets are available from our homepage www.teknos.com. All trademarks displayed on this document are the exclusive property of Teknos Group or its affiliated companies.